

Color shown is 700 Café



Costa D'Avorio | ceramic tile



Costa D'Avorio

Features

- Ceramic floor/wall combo offering three subtle colors with substantial veining
- Sophisticated visual includes a pale bone that's a fresh new look with heavy graining in greys, the season's hottest color family
- · Great look at entry level price point

Colors

- 100 Bone white and pale grey swirled with grey veining; pale beige undertones — Coordinates with existing style CS22A, Colonnade Mosaic, colors 101 or 201
- 200 Beige Honeyed tones with grey and brown veining Coordinates with existing style CS22A, Colonnade Mosaic, color 200
- 700 Café Creamy latte in the taupe range, with mocha and grey veining Coordinates with existing style CS22A, Colonnade Mosaic, color 200



100 Bone



200 Beige



700 Café

Tile Sizes

Field Tile

3" × 3"	CS09F
7" × 7"	CSIOF
10" × 13 " Wall Tile	CSIIF
Trim	
3" x 13" Bullnose	CSI2F
2" × 10" Wall Bullnose	CS13F
Accent	
4" x 8" Wall Listello	CSI4F

Technical

Wear Rating Group	4
Break Strength	304/412 lbs.
Water Absorption	6%
COF (Wet)	0.70

This tile features random variations of shade and texture within each carton. To insure optimum appearance, it is imperative that tiles from various cartons be continually blended during installation. Placement of tiles should be decided on before beginning installation.

*OSHA (Occupational Safety and Health Administration) has established a recognized industry standard of 0.5 (wet and dry) for slip-resistant surfaces. The Americans with Disabilities Act (ADA) recommends, but does not require, "a Static Coefficient of Friction of 0.60 for accessible routes and 0.80 for ramps." ADA does not specifically state that 0.60 is both a dry and a wet requirement. It is important to note that any tile or other hard surface flooring can become slippery when wet or improperly maintained. Products installed in an exterior application must comply with applicable ANSI 108 series of the "American National Standard Specifications for the Installation of Ceramic Tile" and comply with TCA installation methods applicable to installation conditions.

Approved Usage



Accents



101 Multi