HOLSAG CANADA

Seating Manufacturer

Specifications: Carlo Stacking Chair

Description

The stylish, modern Carlo chair is unbeatable in its good value. This stacking chair is built to withstand constant use so it is suited for many high traffic areas such as schools, conference rooms and restaurants.

Dimensions

Height	31.5"	80 cm
Depth	19"	48.3 cm
Width	19"	48.3 cm
Seat Width	16.25"	41.3 cm
Seat Depth	16"	40.6 cm
Seat Height	18"	46 cm
Chair Weight	12.8 lbs	5.8 kg
Carton Weight		
with 1 chair	22.8 lbs	10.3 kg
with 2 chairs	35.6 lbs	16.2 kg
Carton Size for 1 Chair		
18.25" x 22.25" x 37.5"		
46 cm x 56 cm x 95 cm		
Carton Volume for 1 Chair		
8.8 cubic feet		
Carton Size for 2 Chairs		
18.25" x 24.5 " x 37.5"		
46 cm x 62 cm x 95 cm		
Carton Volume for 2 Chairs		
9.7 cubic feet		
Note: Packing of chairs is based on		
the shipping method.		

The Carlo chair stacks well to six chairs high.

Wood

Species: 100% European Beech (uniform layers inside and out)

Legs: Made of 14 plys to a finished thickness of 1 1/16".

Seat and back supports: Made of 15 plys with a finished thickness of 1 1/16".

Leg rail: Made of 13 plys with a finished thickness of 3/4".

Seat panel: Made of 8 plys to a finished thickness of 3/8". The front edge is rounded for comfort.

Chair back: Made of 8 plys to a finished thickness of 3/8".

Construction

The chair is reinforced with metal to metal hardware and reinforced with high solids glue.

Finish

Current standard wood colors are Natural and Black and Cherry.

8-Step Finishing Process

- 1. The bare wood components of the chair are thoroughly sanded using 120 grit paper.
- 2. One coat of stain is sprayed onto all sides of the wood components.
- 3. The chair components are inspected and any necessary color adjustments made.

- 4. One coat of a nitrocellulose sealer is sprayed onto all wood parts to completely seal the wood.
- 5. Once dry, the sealer is sanded using 320 grit paper.
- 6. A nitrocellulose lacquer is sprayed on.
- 7. The wood components are then assembled.
- 8. A final inspection is performed prior to packaging to ensure a high level of quality control.



Note: Specifications are subject to change without notice.

Holsag Canada

164 Needham Street Lindsay, Ontario Canada K9V 5R7 (705) 878-1970 (888) 745-0721 (U.S. & Canada) Fax: (705) 878-1864

www.holsag.com